

Longcester® LF720

Fluoropolyer resin

Product Data Sheet

General Description

LF720 is FEVE type fluoropolyer

- ·Excellent chemical resistance
- ·Excellent wethering resistance
- ·Good flow and matt gloss effect
- ·Outstanding mechanical properties
- ·200C standard cure. Good storage stability

Product Specifications		
Property	Range	Test Method
Appearance	clear granule	Visual
Viscosity	30~40 pa.s	ASTM D4287
OH value	40~45 mg KOH/g	Longcai method
Color	Max 5	ASTM D1544
Tg	appr. 56	DSC

Extrusion & Application Conditions Extruder: Lingyu SLJ-20

Zone II temp.: $85^{\circ}105^{\circ}\mathbb{C}$ Zone II temp.: $90^{\circ}105^{\circ}\mathbb{C}$ Screw speed: $400^{\circ}500$ rpm

Panel: 0.7mm pre-treated cold-rolled steel

Spray gun: Lingyu SJ-5 Voltage: 60~90kV

Curing cycles: 10 min. @ 200 ℃

Starting Formulation	
Component	Weight
LF720	83.0
LC-1530	17.0
Titanium dioxide	50.0
LC-88 Flow agent	1.5
Benzoin	0.5

Packaging

- · White PE bag, N.W.25kg/bag, 1000kg/pallet.
- · Big bags 750 kg

Storage

The product can be stably stored for at least one year when kept in closed containers in a dry place at temperature below 30 $^{\circ}$ C. Avoid exposure to direct sunlight.

Film Properties		
Item	Result	Test Method
Film thickness, µm	approx. 60	ASTM D1186
Gloss @ 60º, %	20~30 unit	ASTM D523
Direct/reverse impact, inch lbs	80/80	ASTM D2794
1/8" Conical mandrel	pass	ASTM D522
Adhesion(cross cut)	5B	ASTM D3359
Pencil hardness	Н	ASTM D3363

Yantai Longcai Advanced Materials Co., Ltd

No.18 Hangzhou Road., Haiyang Development Zone, Yantai, China Post code: 265100 Tel.: +86 535-330 6639 Web-site: www.longcester.com Fax: +86 535-330 6828

ongcester.com E-mail: info@longcester.com

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use. LONGCAI MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.