



## Longcester<sup>®</sup> LC-308

### Antistatic Agent for Powder Coatings

#### General Description

LC-308 alters the conductivity of the powder coating and improved application and quality. Improve the application coverage.

- Effective in recessed areas by minimizing Faraday-Cage effects
- Improved flow during application
- Recommended levels:0.1~0.3% (total formulation)

#### Product Specifications

Property	Range	Test Method
Appearance	White powder	Visual
Particle size distribution(D50)	900 micron	ISO 3001
Melting Range ( °C )	67~71	ISO11357-1
Volatile	<1.0%	Longcai method