

LongCester® P 3502

Saturated carboxylated polyester resin

General Description

LongCester® P 3502 is a medium reactivity polyester resin, designed for 50:50 hybrid powder coatings. Coatings based on it exhibit:

- Special purpose of wrinkle finish
- Medium cure
- Good mechanical performance
- Easy adjust wrinkle finish effect

Extrusion & Application Conditions

Extruder:	Lingyu SLJ-20
Zone I temp.:	85~105 C
Zone II temp.:	90~110 C
Screw speed:	300~400rpm
Panel:	0.5mm pre-treated cold-rolled steel
Spray gun:	Lingyu JP-80
Voltage:	60~90kV
Curing cycles:	10 min. @ 200 C

Packaging

- White PE bag, N.W.25kg/bag, 1000kg/pallet.
- Big bags 750 kg.

Storage

The product can be stably stored for at least one year when kept in closed containers in a dry place at temperature below 30 C . Avoid exposure to direct sunlight.

Product Specifications

Property	Range	Test Method
Appearance	Clear granules	Visual
Acid value, mgKOH/g	70~75	ASTM D1639
Viscosity @ 175 C , mPa·s	30~40 pa.s	ASTM D4287
Gardner Color(50% solution)	max.10	ASTM D1544

Other Data

Property	Range	Test Method
Glass transition temp., C	approx. 58	DSC

Starting Formulation

Component	Weight %
LongCester® P 3502	300.0
KD-213	300.0
Titanium dioxide	300.0
Wrinkle agent	1.5
Benzoin	3.0
CaCO3 filler	95.5

Film Properties

Item	Result	Test Method
Film thickness, μm	approx. 90	ASTM D1186
Gloss @ 60°, %	32 unit	ASTM D523
Direct/reverse impact, inch lbs	80/80	ASTM D2794
1/8" Conical mandrel	pass	ASTM D522
Adhesion(cross cut)	5B	ASTM D3359
Pencil hardness (Mar)	H	ISO 15184-98

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use. LONGCAI MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.